Revised January 2002



9411 Corsair Road Frankfort, IL 60423 1-800-552-0299 Phone 1-815-464-5650 Fax

# EMERGENCY PHONE 1-800-255-3924 TECHNICAL DATA SHEETS RP5L

#### **Description:**

Medium setting: general purpose adhesive designed to bond a wide variety of similar or dissimilar materials. The product is a versatile adhesive offering good climatic, thermal and impact resistance. It's elasticity makes it ideal for bonding dissimilar materials. Handling strength in 10 to 15 seconds. RP 5L has a viscosity of 5 cps and is capable of filling gaps up to. 005.

### **Physical Properties:**

COLOR: Clear
VISCOSITY: 5cps
BASE: Ethyl
STRENGTH: 2700 / 4300
TEMPERATURE RANGE: -65 - 200°F
CURE SPEED: 10 seconds
(FIXTURE)
FULL CURE: 8 hours
MIL A 46050 Type II

MIL A 46050 Type II
Class I
SPECIFIC GRAVITY 1.05

SOLUBLE IN: Remove Debonder

## **Handling Characteristics:**

ling Characteristics:			
Shear Strength, ASTM D1002, DIN 53283		Value	Range
Girt Blasted Steel, N/mm^2 (psi)		28 (3770)	24 to 32 (3195 to 4355)
Etched Aluminum, N	/mm^2 (psi)	20 (3770)	16 to 24 (3195 to 4355)
ABS, N/mm^2	(psi)	>7 (>885)	
PVC, N/mm^2	(psi)	>5 (>640)	
Polycarbonate, N/mm *	^2 (psi)	>6 (>825)	
Phenolic, N/mm^2	(psi)	12 (160)	6 to 18 (775 to 2450)
Neoprene rubber, N/n *	nm^2 (psi)	>12 (>1600)	
Nitrile rubber, N/mm/*	^2 (psi)	>12 (>1600)	
Tensile Strength, ASTM D2095, DIN 53283			
Grit Blasted Steel, N/	mm^2 (psi)	20 (3000)	14 to 28 (1900 to 4000)

\* Substrate Failure

NON-WARRANTY: Information contained herein is based on tests we believe to be reliable and accurate. It is offered in good faith for the benefit of the consumer. Adhesive Systems shall not be liable for any injury, loss, or damage in the use of it's chemical products since the conditions of use are beyond our control. In every case we urge and recommend the user conduct tests to determine to their own satisfaction that the product is of acceptable quality and is suitable for their particular purpose under their own operating conditions. Statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Because of changing reporting requirements and other variables it is impossible to guarantee the accuracy of the information contained in this document. It is the responsibility of the user to determine proper personal protection based on the actual condition of use and to comply with all Federal, State, and Local laws and regulations.

## **Engineering Excellence**

For technical information and support call 1-800-552-0299 or visit our website at

