

# MAXIMUM PERFORMANCE SERVES MP531005E UV ADHESIVE

TECHNICAL DATA SHEET TDS #: MP531005E UV Adhesive

### DESCRIPTION

MP531005E is a high performance UV curing adhesive engineered to bond metals and plastics. It can be used in a variety of product assemblies and it promotes innovative design solutions. Our MP531005E is a leading performer when used for electronic and general industrial applications. This maximum performance adhesive has a deep cure and great flexibility. During in-line inspection this adhesive flouresces a blue color when using a low intensity black light. MP531005E is often cured with an electroless lamp D, medium pressure metal halide lamp. This UV adhesive also works well with UV light emitted diodes (UV LED) at wavelengths of 365 nm to 395 nm. Design engineers select MP5321005E for the optimum in finished product quality, reliability, performance, and cost effectiveness. MP531005E is an essential tool in improving overall product quality, lowering per unit cost, and reducing processing time.

### PHYSICAL PROPERTIES (UNCURED):

Chemical Class Acrylate Solvent Content None

Appearance Colorless Liquid

Density, g/ml 1.05

Viscosity, 25 °C, 20 RPM 500cp-1000cp

Flash Point °C 95

### PHYSICAL PROPERTIES (CURED):

| <b>Durometer Hardness</b>         | D30        |
|-----------------------------------|------------|
| Water Absorption, 2 hrs. @100 °C  | 4.7%       |
| Water Absorption, 24 hrs. @ 25 °C | 4.9%       |
| Glass Transition Temperature, °C  | 19         |
| Lap Shear Strength PSI Polycarb.  | 810        |
| Dielectric Constant               | 3.2        |
| Dielectric Strength, volts/mil    | >400       |
| Working Temperature °F            | -60 to 300 |
| Flexibility@RT                    | Yes        |
| Blue Flourescing                  | Yes        |

# **Benefits**

- Superior Bond Strength
- Solvent Free
- Low Odor
- Improves Finished Product Quality
- Durable
- Good Impact and Vibration Resistance
- Easily Automated
- No Clean Up

### **Substrate Applications**

Plastics Metal

## CURE SCHEDULE

Medium Pressure Metal Halide Flood Lamp Station @ 50mW/cm2 Fusion F 300 S Lamp D Conveyor @ 750 mW/cm2 Fixed time between 2 Glass Slides @ low intensity black light Cure Depth @ 50 mW/cm2 for 2 minutes UV LED 365 nm to 395 nm

40 seconds Belt Speed @ 20 FPM 1 second 0.7 inch

Time depends on the intensity and wavelength

# Storage and Shelf Life

This UV Cure material should be stored in a dark place, above 0°C and below 30 °C. The shelf life is one year from the date of manufacture.



# Engineering Excellence

For technical information and support call 1-800-552-0299 or visit our website at



# **Directions for Use**

- 1. This product cures at exposure to daylight. Minimize to expose during storage and handling.
- 2. Surface of substrates should be clean and free from grease, mold release, or other contaminants.
- 3. Cure speed is dependent on UV energy, intensity of UV Light, required depth of cure and percentage of light transmission of substrates.
- 4. For the best performance, Fusion Lamp D or medium pressure metal halide should be used. Also, UVLED at 365 nm to 395 nm can be used.
- 5. Allow cured parts to cool before testing to any service loads.
- 6. Air inhibits a surface cure. To minimize this effect an inert gas such as nitrogen can be used or a higher intensity can be used.