


**Figure 1 – Berghaus and Wingina location map**



**Figure 2 – Berghaus prospect diamond drilling location plan (Rugby holes in red)**





Figure 3 – Wingina Long Section



**Table 1 – Preliminary Drill Intercepts >1.0 g/t Gold**

HOLE	SIGNIFICANT ASSAYS RESULTS	REMARKS
DD001	22.6 to 24.6 = 2.0m @ 1.28 g/t Au 27.2 to 28.1 = 0.9m @ 1.24 g/t Au 30.8 to 31.6 = 0.8m @ 2.81 g/t Au <b>47.2 to 47.7 = 0.5m @ 11.9 g/t Au*</b> 50.6 to 51.6 = 1.0m @ 1.22 g/t Au 55.6 to 56.1 = 0.6m @ 1.96 g/t Au	Visible Au 47.4 to 47.7m  * currently bring re-assayed  Check assays awaited
RDD002	<b>15.5 to 16.5 = 1.0m @ 17.4 g/t Au</b> 19.6 to 21.7 = 2.1m @ 1.97 g/t Au 23.6 to 24.8 = 1.2m @ 1.26 g/t Au 28.5 to 29.0 = 0.5m @ 1.84 g/t Au	Visible Au at 15.6m  Check assays awaited
RDD002B	<b>10.9 to 16.2 = 5.3m @ 2.66 g/t Au</b> 22.0 to 23.5 = 1.1m @ 2.10 g/t Au 32.0 to 33.0 = 1.0m @ 1.51 g/t Au	Check assays awaited
RDD003	6.6 to 7.0 = 1.1m @ 1.3 g/t Au 20.1 to 26.7 = 6.6m @ 4.01 g/t Au <b>inc 20.1 to 23.5 = 3.4m @ 6.25 g/t Au</b>	Check assays awaited
RDD004	5.0 to 6.0 = 1.0m @ 1.03 g/t Au <b>10.0 to 11.0 = 1.0m @ 4.29 g/t Au</b>	Check assays awaited
RDD005	25.0 to 26.0 = 1.0m @ 1.33 g/t Au 30.0 to 38.0 = 6.0m @ 1.81 g/t Au <b>inc 33.0 to 34.0 = 1.0m @ 4.74 g/t Au</b>	Check assays awaited
RDD006	14.0 to 16.0 = 2.0m @ 2.84 g/t Au 48.0 to 49.0 = 1.0m @ 3.51 g/t Au 60.0 to 65.7 = 5.7m @ 5.18 g/t Au <b>inc 63.2 to 64.6 = 1.4m @ 16.05 g/t Au</b>	Check assays awaited
RDD007	No significant results	Check assays awaited
RDD008	26.0 to 27.0 = 1.0m @ 1.05 g/t Au <b>43.0 to 43.5 = 0.5m @ 10.7 g/t Au</b>	Check assays awaited

**Table 2 - Drill Hole Details**

HOLE	MGA E	MGA N	RL (m)	DEPTH	AZ (MAG)	DIP
RDD001	657006	7700221	83	90.4	323	-60
RDD002	657038	7700238	84	74.9	323	-60
RDD002B	657036	7700241	81	36.5	323	-60
RDD003	657131	7700318	81	69.1	323	-60
RDD004	657164	7700340	81	69.9	323	-60
RDD005	657074	7700250	81	62.2	323	-60
RDD006	657369	7700472	84	81.4	323	-60
RDD007	657401	7700493	79	102.5	323	-60
RDD008	657650	7700596	77	53.8	143	-60

## Quality Control and Assurance

All drilling was completed by Mount Magnet Drilling using a SD1000 diamond core drill, with HQ3-sized core and triple-tube used throughout the program. All samples were stored in plastic core trays in a dedicated core yard at the company's field camp. All core was photographed, geologically and geotechnically logged prior to core cutting and sampling being undertaken. Core orientation using a Reflex Act II rapid descent core orientation instrument was utilized on selected intervals on all holes.

ALS Laboratory Services Pty Ltd in Perth undertook sample preparation using their PREP-31B technique (drying, crushing, and pulverizing), before assaying for gold via their Au-AA26 technique in which a 50g charge was split from each sample for fire assay with an AAS finish.

Rugby has implemented a quality control (QA/QC) program which includes insertion of blanks, certified reference material standards (CRM) and duplicate samples in order to ensure best practice in sampling and analysis. Actual CRM submission rate is 1:20, blank submission rate is 1:20, coarse crush (-2mm) duplicate submission rate is 1:20, pulverized (-75um pulp) duplicate submission rate is 1:20 and check lab pulp duplicate submission rate is 1:20. Check assaying is currently underway at Intertek-Genalysis Laboratory Services Pty Ltd). All CRM material was acquired from Geostats Pty Ltd and values range from 0.18 – 6.88 g/t Au. ALS and Intertek are ISO-9001:2000 certified laboratories.

Drilling was orientated approximately N35°W (325°) SE and perpendicular to the strike of the mineralizing structures. The orientation of the drilling is considered adequate for an unbiased assessment of the prospect with respect to interpreted structures and interpreted controls to mineralisation. The diamond drilling program comprised 640.7m in eight holes (RDD001 - RDD008), and these have been logged in their entirety. Overall core recoveries for the total drilling programme were calculated at 96%. Assay results reported are down-hole length weighted averages of grades above 1.0 g/t Au. Short intervals of high grade internal to the broader zones of gold mineralization are reported as included intervals with from and to depths recorded. No top cuts have been applied to the reporting of the assay results.

Francisco Montes, Rugby's Chief Geologist and a "qualified person" ("QP") within the definition of that term in National Instrument 43-101, Standards of Disclosure for Mineral Projects, has verified the technical information that forms the basis for this news release.